

**EFFECTS OF CHROMIUM POWDER MIXED IN ELECTRICAL
DISCHARGE MACHINING OF AISI D2 HARDENED STEELS**

MUHAMMAD RIDZUAN BIN IDRIS

Project dissertation submitted in partial fulfilment of the requirement for the Master's
Degree in Mechanical Engineering

Faculty of Mechanical and Manufacturing Engineering

Universiti Tun Hussein Onn Malaysia

APRIL, 2015

This research is dedicated to my family especially to my father, Encik Idris bin Jusoh and my late mother, Puan Kamariyah Hasan, thank you for the support, encouragement and spiritual, also thanks to my supervisor, Assoc. Prof. Dr. Mohd Amri Bin Lajis for the guidance, opinions and advices.

Thanks for all the advices, supports and love.



ACKNOWLEDGEMENTS

Firstly, I would like to thank ALLAH S.W.T for blessing me to complete for this project within the given period of time. My deepest thank to my beloved parents and family for their encouragement and spiritual. I also would like to thank all my friends, for their generosity and kindness in helping me to giving the new ideas, opinions, sharing the knowledge's, suggestion and the supports.

A very special appreciation goes to my supervisor, Assoc. Prof. Dr. Mohd Amri Bin Lajis, for their guidance, patience and endless encouragement throughout this project. Under guidance of him, I have been able to finish my project within the scope of works and to achieve the objectives of this project.

Furthermore I would also like to acknowledge with much appreciation the crucial role of the technician of Material Science Lab and Microelectronics and Nanotechnology - Shamsuddin Research Centre (MiNT-SRC), who gave the permission to use all required equipment and the necessary material to complete the all research task. Special thanks go to my friends, who help me to assemble the parts and gave suggestion to finish this thesis. I would also like to thank to Exploration Research Grant Support (ERGS) Foundation for their financial support granted through Graduate Research Assistant Scheme.

A lot of thank to all the contributors whose names have been missed out in the list of acknowledgement.

ABSTRACT

Nowadays, electrical discharge machining (EDM) is the non-conventional method that has been used extensively in machining hard material that is commonly used in mold and die industry but the limitations of EDM will cause lower productivity and poor surface quality. EDM becomes most apparent by using powder metallurgy electrode together with chromium (Cr) powder suspension into the dielectric fluid which has led to the increasing of productivity and good quality performance and characteristics. Therefore, by combining of both EDM parameters and machining conditions by incorporating with specific magnetic system plus integrated with existing filter system, it is highly expected that the machining speed can be enhanced. However, there are difficulties to determine the best combination of these machining parameters in order to increase the material removal rate (MRR) and at the same time to reduce the electrode wear rate (EWR) with the acceptable surface integrity. This research emphasizes the studies of Cr powder mixed in EDM machining of AISI D2 hardened steel using copper tungsten electrode which has been done successfully. Data were analysed using design of three factors at a time consisted of peak current (I_p), pulse-on (P_{on}) and powder concentration (C). Discussions were made on the responses such as MRR, EWR, Surface Roughness (R_a), surface morphology, recast layer (R_L) and microhardness (MH) on the selected samples from the same machining conditions. Results have proved that I_p was the most significant parameter which has influenced the machining responses on Cr powder mixed EDM of AISI D2. It is also found that proper powder concentration of 2gram/litre enhanced the machining efficiency particularly in MRR. Furthermore, introduction of proper addition of Cr powder in the dielectric also decreased R_a and R_L thickness. The EWR increased as the peak current increased, but inversely with pulse-on. In general, the possibility of EDM process for machining AISI D2 tool steel by incorporating Cr powder mixed in the dielectric is acceptable and the entire objectives were successfully proven.

ABSTRAK

Pada masa kini, mesin nyahcas elektrik (EDM) adalah satu kaedah tidak-konvensional yang telah digunakan secara meluas di dalam pemesinan bahan keras yang lazimnya digunakan dalam industri acuan tetapi kekurangan yang ada pada EDM akan menyebabkan pengeluaran produktiviti yang rendah dan kualiti permukaan pemesinan yang tidak baik. EDM akan menjadi lebih baik dengan menggunakan elektrod jenis serbuk metalurgi bersama-sama dengan campuran serbuk kromium (Cr) ke dalam cecair dielektrik yang boleh meningkatkan produktiviti dan menghasilkan ciri-ciri pemesinan yang berkualiti. Oleh yang demikian, dengan gabungan kedua-dua parameter EDM tersebut ditambah pula dengan sistem magnet yang menggantikan penapis sedia ada dijangka meningkatkan kelajuan pemesinan. Walau bagaimanapun, terdapat kesukaran untuk menentukan kombinasi parameter yang paling baik untuk meningkatkan kadar pembuangan bahan (MRR) dan pada masa yang sama mengurangkan kadar haus elektrod (EWR) dengan integriti permukaan yang boleh diterima. Kajian campuran serbuk Cr dalam cecair dielektrik diuji dengan keluli keras AISI D2 sebagai bahan kerja dan menggunakan kuprum tungsten sebagai elektrod telah dilakukan dengan jayanya. Data akan dianalisis menggunakan reka bentuk daripada tiga faktor iaitu arus puncak (I_p), kadar denyutan (P_{on}) dan kepekatan campuran (C). Tindak balas seperti MRR, EWR, kekasaran permukaan bahan (R_a), morfologi, lapisan kesan pemanasan haba (R_L) dan mikrokeras hasil dari sampel yang dipilih dari keadaan pemesinan sama akan dibincangkan. Keputusan menunjukkan bahawa I_p adalah parameter yang paling berkesan mempengaruhi pemesinan. Ia juga mendapati bahawa tambahan serbuk Cr akan membantu meningkatkan kecekapan pemesinan terutamanya dalam keputusan MRR. Campuran serbuk Cr dengan kuantiti optimum sebanyak 2gram/liter ke dalam dielektrik akan mengurangkan R_a dan R_L . Selain itu, EWR meningkat kerana peningkatan arus tetapi menurun jika masa denyutan ditambah. Secara umumnya, sesuatu proses EDM untuk pemesinan keluli AISI D2 dengan serbuk Cr dicampur dalam dielektrik boleh diterima dan keseluruhan objektif telah terbukti.

TABLE OF CONTENTS

TITLE	i
DECLARATION	ii
DEDICATION	iii
ACKNOWLEDGEMENT	iv
ABSTRACT	v
ABSTRAK	vi
TABLE OF CONTENTS	vii
LIST OF FIGURES	xii
LIST OF TABLES	xvii
LIST OF ABBREVIATIONS AND SYMBOLS	xix
LIST OF APPENDICES	xxi
CHAPTER 1	INTRODUCTION
1.1	Overview
1.2	Background of Study
1.3	Problem Statement
1.4	Objective
1.5	Scope
1.6	Hypothesis

CHAPTER 2	FUNDAMENTAL OF ELECTRICAL	9
	DISCHARGE MACHINING (EDM)	
2.1	Introduction	9
2.2	Principle of EDM Process	11
2.2.1	Generator Design	12
2.2.2	EDM Control System	14
2.2.3	EDM Process Mechanism	15
2.3	EDM Parameter	17
2.3.1	Electrical Parameter	18
2.3.1.1	Peak Current	18
2.3.1.2	Pulse duration	20
2.3.1.3	Frequency	21
2.3.1.4	Polarity	22
2.3.1.5	Discharge Voltage	23
2.3.2	Non-Electrical Parameter	24
2.3.2.1	Dielectric	24
2.3.2.1	Flushing	25
2.3.3	Powder Mixed EDM	26
2.4	Electrode	30
2.4.1	Metallic Electrodes	32
2.4.1.1	Copper	32
2.4.1.2	Tungsten	33
2.4.1.3	Copper Tungsten	34

2.4.1.4	Brass	36
2.4.1.5	Silver	36
2.4.2	Graphite Electrodes	37
CHAPTER 3	LITERATURE RIVIEW	39
3.1	Introduction	39
3.2	The Fabrication of AISI D2 Hardened Steel	40
3.3	EDM Machining of Hardened Steels	42
3.4	EDM Machining of AISI D2 Hardened Steels	44
3.5	Powder Mixed of EDM machining	55
3.6	Summary	63
CHAPTER 4	METHODOLOGY	66
4.1	Research Design Principles	66
4.1.1	Higher peak current, pulse duration employed for higher MRR and productivity	68
4.1.2	Filtering system	68
4.1.3	Chromium powder as suspended material	70
4.2	Experimental design and variables	71
4.2.1	Machining parameters	71
4.2.2	Machining characteristic	73
4.3	Research procedures	79
4.3.1	Machining Setup	80

4.3.2	Powder Metallurgy Electrode	85
4.4	Equipment and instrumentation	86
4.4.1	Major Instrument	87
4.4.2	Measuring Instruments	88
4.4.2.1	Digital weighting balance	89
4.4.2.2	Surface Roughness Tester	90
4.4.2.3	Tool Maker Microscope	91
4.4.2.4	Scanning Electron Microscope	92
4.4.2.5	Vickers hardness tester	94
4.5	Specimen preparation	95
4.5.1	Sectioning	97
4.5.2	Mounting of specimens	99
4.5.3	Grinding	100
4.5.4	Polishing	101
4.5.5	Etching	103
CHAPTER 5	RESULTS AND DISCUSSION	106
5.1	Material Removal Rate (MRR)	108
5.2	Electrode Wear Rate (EWR)	112
5.3	Surface Roughness (R_a)	117
5.4	Surface Integrity	128
5.4.1	Recast Layer (R_L)	128
5.4.2	Microhardness (MH)	139

CHAPTER 6	CONCLUSION	144
	REFERENCE	147
	APPENDIX	158



LIST OF FIGURES

1.1	Classification of EDM research	2
2.1	Schematic of conventional EDM process	12
2.2	Relaxation circuit	13
2.3	Variation of capacitor voltage with time	13
2.4	EDM spark sequence	15
2.5	Illustration of different usage of current to the different surface area	19
2.6	Pulse-on with different duty cycle	20
2.7	Pulse-on with different frequency	21
2.8	EDM polarity	22
2.9	Actual profile of a single EDM pulse	23
2.10	Schematic diagrams of the electric discharge for single power pulse	27
2.11	The material removal mechanism during the normal discharge for the working fluid	28
2.12	Mechanism of PMEDM	28
2.13	Additive particle behavior	28
2.14	PMEDM spark sequence	29
2.15	Copper electrode	33
2.16	Tungsten electrode	33
2.17	Copper Tungsten electrode	35
2.18	Brass electrode	36
2.19	Silver electrode	37
2.20	Graphite electrode	38

3.1	EDM setup using CNT	49
3.2	PMEDM schematic for dispenser and pump system.	50
3.3	Diagram of a self-designed filter system for the EDM.	52
3.4	Typical waveform of voltage and current:	59
3.5	Discharging waveform of voltage	60
3.6	The apparatus used to produce a single discharge	61
3.7	Comparison of crater morphology at various machining parameters	62
3.8	Micrographs of crater generated by a single pulse discharge	63
4.1	Overall research methodology	67
4.2	Illustration of powder and debris motion in PMEDM process	69
4.3	Ishikawa Cause-Effect Diagram	72
4.4	Two categories of machining characteristic	73
4.5	Specimen test preparation	74
4.6	Experimental process flowchart	79
4.7	Experiment setup for HPEDM	81
4.8	Image for HPEDM	84
4.9	Sodick AQ55L	88
4.10	Mettler Toledo PL403 precision balance.	89
4.11	Mahr Perthometer PGK-120	90
4.12	Tool Maker Microscope Nikon MM-60	91
4.13	Scanning Electron Microscope (Joel-JSM 6380 L.V)	93
4.14	Vickers tester	95
4.15	Specimen preparation	97
4.16	Abrasive cut-off machine (Stuers Lobotom 3)	98
4.17	Specimens after compression mounting	99
4.18	Buehler Auto Mounting Press machine	100

4.19	Buehler Roll Grinder	101
4.20	Polish machine	102
4.21	Bright field illumination	104
4.22	Dark field illumination	105
5.1	Effect of powder concentration and pulsed duration on material removal rate [$I_p=20A$]	110
5.2	Effect of powder concentration and pulsed duration on material removal rate [$I_p=32A$]	110
5.3	Effect of powder concentration and pulsed duration on material removal rate [$I_p=40A$]	110
5.4	Effect pulsed duration and powder concentration on electrode wear rate [$I_p=20A$]	114
5.5	Effect pulsed duration and powder concentration on electrode wear rate [$I_p=32A$]	114
5.6	Effect pulsed duration and powder concentration on electrode wear rate [$I_p=40A$]	114
5.7	Surface morphology of electrode with different pulse-on	116
5.8	Effect pulse duration and powder concentration on surface roughness [$I_p=20A$]	119
5.9	Effect pulse duration and powder concentration on surface roughness [$I_p=32A$]	119
5.10	Effect pulse duration and powder concentration on surface roughness [$I_p=40A$]	119
5.11	Surface morphology of D2 workpiece at increasing peak current [$P_{on}=50\mu s$, $C=2g/l$]	121
5.12	Surface morphology of D2 workpiece at increasing pulse-on [$I_p=20A$, $C=2g/l$]	123
5.13	Surface morphology of D2 workpiece at an increasing powder concentration [$I_p=40A$, $P_{on}=50\mu s$]	125
5.14(a)	Surface texture of EDM workpiece for maximum and minimum surface roughness	127

5.15	Effect Pulse-on and Powder concentration on Recast layer at Peak current [$I_p=20A$]	130
5.16	Effect Pulse-on and Powder concentration on Recast layer at Peak current [$I_p=32A$]	130
5.17	Effect Pulse-on and Powder concentration on Recast layer at Peak current [$I_p=40A$]	130
5.18(a)	Optical microscope showing the cross-sectional view of the recast layer of the EDM machined surface layer [$P_{on}=100\mu s$, $C=2g/l$, $I_p=20A$]	132
5.18(b)	Optical microscope showing the cross-sectional view of the recast layer of the EDM machined surface layer [$P_{on}=100\mu s$, $C=2g/l$, $I_p=40A$]	132
5.18(c)	SEM showing the cross-sectional view of the recast layer of the EDM machined surface layer [$P_{on}=100\mu s$, $C=2g/l$, $I_p=20A$]	133
5.18(d)	SEM showing the cross-sectional view of the recast layer of the EDM machined surface layer [$P_{on}=100\mu s$, $C=2g/l$, $I_p=40A$]	133
5.19(a)	Optical microscope showing the cross-sectional view of the recast layer of the EDM machined surface layer [$P_{on}=50\mu s$, $C=0g/l$, $I_p=32A$]	134
5.19(b)	Optical microscope showing the cross-sectional view of the recast layer of the EDM machined surface layer [$P_{on}=100\mu s$, $C=0g/l$, $I_p=32A$]	134
5.19(c)	SEM showing the cross-sectional view of the recast layer of the EDM machined surface layer [$P_{on}=50\mu s$, $C=0g/l$, $I_p=32A$]	135
5.19(d)	SEM showing the cross-sectional view of the recast layer of the EDM machined surface layer [$P_{on}=100\mu s$, $C=0g/l$, $I_p=32A$]	135

5.20(a)	Optical microscope showing the cross-sectional view of the recast layer of the EDM machined surface layer [$P_{on}=75\mu s$, $C=0g/l$, $I_p=20A$]	137
5.20(b)	Optical microscope showing the cross-sectional view of the recast layer of the EDM machined surface layer [$P_{on}=75\mu s$, $C=2g/l$, $I_p=20A$]	137
5.20(c)	SEM showing the cross-sectional view of the recast layer of the EDM machined surface layer [$P_{on}=75\mu s$, $C=0g/l$, $I_p=20A$]	138
5.20(d)	SEM showing the cross-sectional view of the recast layer of the EDM machined surface layer [$P_{on}=75\mu s$, $C=2g/l$, $I_p=20A$]	138
5.21	Microhardness of Sub-surface layer of workpiece at different Powder concentration [$I_p=40A$, $P_{on}=100\mu s$]	140
5.22	Microhardness of Sub-surface layer of workpiece at different Peak current [$C=2g/l$, $P_{on}=100\mu s$]	141
5.23	Microhardness of Sub-surface layer of workpiece at different Pulse-on [$I_p=40A$, $C=2g/l$]	143

LIST OF TABLES

2.1	Advantages and limitations of EDM	10
2.2	Electrode material properties that effect EDM	31
2.3	Physical properties and miscellanea of copper and tungsten	35
3.1	Chemical composition of AISI D2 hardened steel	40
3.2	Physical properties of AISI D2 hardened steel	40
3.3	Procedure of heat treatment for AISI D2 hardened steel	41
4.1	Specifications of powder used	70
4.2	Thermophysical properties of powder used	70
4.3	Machining parameter	72
4.4	Experimental Design and Response	75
4.5	Data collection sample of material removal rate of each composition of powder concentration and peak current (I_p) setting	76
4.6	Data collection sample of tool wear rate of each composition of powder concentration and peak current (I_p) setting	77
4.7	Data collection sample of surface roughness of each composition of powder concentration and peak current (I_p) setting	78
4.8	Data collection sample of average micro-hardness of each composition of powder concentration and peak current (I_p) setting	78
4.9	Summary PMEDM part	82

4.10	The specification of Nikon MM-60 (Tools Maker Microscope)	92
4.11	The specification of SEM (JSM 6380)	93
5.1	Overall Result of EWR, MRR, R_a and R_L with different peak current, pulsed on duration and powder concentration	107
5.2	Results of material removal rate (MRR) with different peak current, powder concentration and pulsed on duration	109
5.3	Result of electrode wear rate (EWR) with different peak current pulsed on duration and powder concentration	113
5.4	Result of surface roughness (R_a) with different peak current, powder concentration and pulsed on duration	118
5.5	Result of Recast Layer (R_L) with different peak current, powder concentration and pulsed on duration	129
6.1	Summary of optimum MRR, EWR and R_a	146



LIST OF ABBREVIATIONS AND SYMBOLS

Al	-	Aluminium
AISI	-	American Iron and Steel Institute
C	-	Powder concentration
CNT	-	Carbon nano tube
Cr	-	Chromium
CV	-	Control valve
CuW	-	Copper tungsten
EDM	-	Electrical discharge machining
EWR	-	Electrode wear rate
FPGA	-	Field-programmable get array
HAZ	-	Heat affective zone
HRC	-	Hardness Rockwell unit for steel
I_p	-	Discharge current
MRR	-	Material removal rate
PMEDM	-	Powder mixed dielectric electrical discharge machining
P_{on}	-	Pulse duration
PLC	-	Programmable logic controller
PM	-	Powder metallurgy
SEM	-	Scanning electron microscopy
SA	-	Surface area
SI	-	Surface integrity
SiC	-	Silicon carbide
TELCO	-	Tellurium copper
R_a	-	Surface roughness
R_L	-	Recast layer

t_m	-	Machining times
W_a	-	Weight of workpiece after machining
W_b	-	Weight of workpiece before machining



LIST OF APPENDICES

Appendix A	List of Publication Related
Appendix B	A Summary of Literature Review on EDM Die Sinking (AISI D2 Hardened Steel)



PTTA UTHM
PERPUSTAKAAN TUNKU TUN AMINAH

CHAPTER I

INTRODUCTION

1.1 Overview

Following the technology of manufacturing today, machining process is dealing with challenges from the marketing demand that needed to requires the use of advanced materials such as composite, super alloys, and hardened steels that are so hard to be machined. The high speed machine that can produce good surface integrity and precise cutting with less tool wear, are among the criteria to use in the advance technology, i.e. aerospace, automotive and medical material. Since it is impossible to use conventional machining of hard material, non-conventional machining such as electrical discharge machining (EDM) is one of the ideal techniques in dealing with these materials including hardened steel.

EDM is generally known as a ‘vertical’, ‘ram’ or ‘sinker’ electrical discharge machining that has been used in the industry over fifty years ago. According to the current world developments, EDM has also increased technology that enables the EDM to produce superficial, thin and compact mechanical elements that are used by the advanced manufacturer. The power supply on a previously effective EDM has improved according to the changes in electric and electronic fields. It is capable to produce more power efficiently, generate various types of waves and high frequency. Due to the

existence of rapidly growing control systems, EDM is suitable for producing work that requires a high level of accuracy. Most of EDM use computer numerically method (CNC) as their programming to communicate with human to improve the machining process.

EDM is a machine that can provide many benefits for high accuracy and precision of machining process. It requires further research to produce a more realistic EDM. Numerous researchers have optimized the process variable to improve the machining workpiece characteristics such as by increasing the material removal rate due to increase in machining speed, increasing the tool life and obtain the best surface integrity. Some of the researchers modified the EDM system to fulfill the requirement global trend of machining process. Figure 1.1 shows some of the research area in EDM.




Figure 1.1: Classification of EDM research (Pandey and Singh, 2010)

High potential of EDM can help to improve productivity in the industry. Productivity is one of the important elements in the industry today. Higher productivity can lead to improved industry performance such as lower average costs, higher profits, higher

wages and improved competitiveness and trade performance. Hence, to fulfill this demand, the machines in the industry must have a high speed productivity including EDM.

1.2 Background of Study

Electrical discharge machining (EDM) is the non-conventional method that has been used extensively in the machining process of hard material that is commonly used in mold and die industry. The basic process of EDM is to remove metal through the action of an electrical discharge energy and high current intensity between the tool (electrode) and the workpiece without physical cutting force. This is one of the advance methods to replace traditional machine method that able to machine difficult-to-cut or hard materials such as titanium, inconel and hardened steel. It can be successfully employed to electrically conductive machine parts regardless of their hardness and toughness. In spite of remarkable process capabilities, limitations such as low volumetric material removal and poor surface quality are associated with EDM (Kansal et al, 2007).

Limitation of EDM will cause lower productivity, which is due to low cutting speed. In that case, researchers of EDM explored a new method to improve the sparking efficiency phenomenon including some modification of experimental concepts and their existing system. The researchers needed to consider the machining process condition and parameters such as discharge voltage, peak current, pulse-on, flushing and dielectric medium before executing the new method of the machining process. To date, most of the studies in EDM have undergone the normal effect of machining process condition which applies low level of machining parameters. Yet, few studies have been implemented in greater current and long pulse-on and at the same time to maintain the EDM machining stability and efficiency to obtain the best material removal rate (MRR), lower electrode wear rate (EWR) and the good performance of the workpiece surface

integrity. Therefore, there is a keen interest to look forward into this new phenomena in EDM machining and hence for greater productivity.

Nowadays, research becomes most apparent by using powder metallurgy electrode together with powder suspension into the dielectric fluid which has increased the productivity, and good quality performance and characteristics. Therefore, by using a combination of both EDM parameters and machining process conditions, and incorporating with the specific magnetic system plus integrated with the existing filter system, it is highly expected that this combination can enhance the machining speed. The filter system integrated with magnetic force is used to separate debris or contaminants from dielectric fluid and hence the efficiency of spark erosion becomes more stable and easy to cut the materials. In order to realize the full potential of new setting of EDM machining by incorporating magnetic and pump system, the new dielectric tank was developed which was integrated with a continuous circulation system.

Many studies have been applied through this process in several types of materials, but lack of work has been carried out to incorporate powder mixed in the EDM machining of AISI D2 hardened steels. It is also found that a comprehensive study in EDM machining of AISI D2 is still scarce. New machining data on the EDM of AISI D2 serves a great significance and could be further exploited especially for hole making operation. Further research on powder mixed EDM machining mechanism and its characteristics of this kind of material is expected to give better rate and efficiency of the machining process. This project was undertaken to study the effect of machining process conditions and incorporated with powder mixed in EDM machining of AISI D2 hardened steels and by employing advanced powder metallurgy electrode of copper tungsten (CuW).

REFERENCES

- Ahsan, A.K., Mohammad Y.A. and Md. Mohafizul H., (2009). A study of electrode shape configuration on the performance of die sinking EDM. *Int J Mech& Mat Eng (IJMME)*, Vol. 4, No.1, 19 - 23.
- Angelo P. C. and Subramanian R. (2008). *Powder Metallurgy: Science, Technology And Applications*, PHI learning private limited India
- Amorim and Weingaertner (2005). The influence of generator actuation mode and process parameters on the performance of finish EDM of a tool steel. *Journal of Materials Processing Technology Volume 166, Issue 3, 20 August 2005, Pages 411–416*
- Beri, N. and Kumar, A., (2011). Optimisation of electrical discharge machining process with CuW powder metallurgy electrode using grey relation theory. *International Journal Machining and Machinability of Materials*, Vol. 9, Nos. 1/2.
- Beri, N., Maheshwari, S., Sharma, C. and Kumar, A., (2008). Performance Evaluation of Powder Metallurgy Electrode in Electrical Discharge Machining of AISI D2 Steel Using Taguchi Method. *International Journal of Aerospace and Mechanical Engineering* 2:3, 167 – 171.
- Beri, N., Maheshwari, S., Sharma, C. and Kumar, A., (2010). Technological Advancement in Electrical Discharge Machining with Powder Metallurgy Processed Electrodes: Review. *Material and Manufacturing Processes*, 25: 1186-1197.

- Charmilles Technologies (1991). *ROBOFORM 100,200,400 Users Manual*. Charmilles Technologies Cooperation. Geneva
- Che haron et al. (2008). Copper and Graphite electrode performance in electrical discharge machining of XW42 tool steel. *Journal of material processing technology*. 201: 570-573
- Chow, H.M.*et al.*, (2000). Study of added powder in kerosene for the micro-slit machining of titanium alloy using electro-discharge machining. *Journal of Materials Processing Technology* 101 (2000) 95±103
- Debdulal Das et al. (2011). Sub-zero treatments of AISI D2 steel: Part I. Microstructure and hardness. *Materials Science and Engineering A* 527 (2010) 2182–2193
- Dewangan, S.K. (2010), Experimental Investigation of Machining Parameters for EDM Using U-shaped Electrode of AISI P20 Tool Steel. *Master Thesis Department of Mechanical Engineering National Institute of Technology Rourkela (India)*
- Fleming, B. (2005). *The EDM How-To-Book*. Fleming Publishing. USA.
- Fuller, John, E., (1996). *Electrical Discharge Machining. ASM Machining Handbook*, vol. 16, pp. 557–564.
- Geels, K. (2006). *Metallographic and Materialographic Specimen Preparation, Light Microscopy, Image Analysis and Hardness Testing*, ASTM International
- German R.M. and Heaney D.F. (2004) *Advances in the Sintering of Titanium Powders*, PM 2004, Vienna, Austria.
- Guitrau, E.B(1997). *The EDM Handbook*. Hanser Gardner Publications, Cincinnati.

- Guu,Y.H., and Hocheng, H., (2001). Effects of workpiece rotation on machinability during electrical discharge machining. *Journal of Material and Manufacturing Processes*, 16 (1), 91–101.
- Guu Y.H., Hocheng H., Chou C.Y., Deng C.S. (2003). Effect of electrical discharge machining on surface characteristics and machining damage of AISI D2 tool steel, *Materials Science and Engineering A358*: 37-43.
- Guu Y.H. (2005). AFM surface imaging of AISI D2 tool steel machined by the EDM process, *Applied Surface Science* 242: 245–250.
- Guu,Y.H., Tsai,K.L., Chen,L.K., (2007). An experimental study on electrical discharge machining of maganese-zinc ferrite magnetic material. *Materials and Manufacturing Processes*, 22, 66 - 70.
- Kumar H., and Davim J.P.(2011). Role of powder in machining of Al-10%SiCp metal matrix composites by powder mixed electric discharge machining, *Journal of Composite Materials, Sage*,45, (2011), 133-151.
- Khan, D.A. (2011). Effect Of Tool Polarity On The Machining Characteristics In Electric Discharge Machining Of Silver Steel And Statistical Modelling Of The Process. *International Journal of Engineering Science and Technology (IJEST)*
- Kansal, H.K *et al.*,. (2007).Effect of Silicon Powder Mixed EDM on Machining Rate of AISI D2 Die Steel. *Journal of Manufacturing Processes Vol. 9/No. 1*
- Kansal, H.K. et al.,(2008). Numerical simulation of powder mixed electric dischar machining (PMEDM) using finite element method. *Mathematical and Computer Modelling* 47 (2008) 1217–1237

- Kansal, H.K. et al., (2005). Parametric optimization of powder mixed electrical discharge machining by response surface methodology. *Journal of Materials Processing Technology* 169 (2005) 427–43.
- Kansal, H.K. et al. (2006). Technology and research developments in powder mixed electric discharge machining (PMEDM). *Journal of Materials Processing Technology* 184 (2007) 32–41
- Karastojkovic and Janjusevic (2003). Hardness and structure changes at surface in Electrical Discharge Machined steel 3840. *Proceedings of 3rd BMC-2003-Ohrid, R. Macedonia*
- Ken, R.(2008). Sinker Electrode material Selection. *EDM Magazine Today*.
- Ken, R.((2011). Filtration Filtration. *EDM Magazine Today*.
- Kiyak and Cakir (2007). Examination of machining parameter on surface roughness in EDM tool of tool steels. *Journal of Material Processing Technology*, 191(200&) 141-144
- Kumar ,H. and Davim,J.P. (2011). Role of Powder in the Machining Al-10%SiC_p of Metal Matrix Compositesby Powder Mixed ElectricDischarge Machining. *Journal of composite materials, Vol. 0, No. 00/2010*
- Klocke, F. Et al.(2004).The effects of powder suspended dielectrics on the thermal influenced zone by electrodischarge machining with small discharge energies. *Journal of Materials Processing Technology* 149 (2004) 191–197
- Kung, K.Y et al (2009). Material removal rate and electrode wear ratio study on the powder mixed electrical discharge machining of cobalt-bonded tungsten carbide. *Int J AdvManuf Technol* (2009) 40:95–104

- Kumar, A et al. (2011). Research Developments in Additives Mixed Electrical Discharge Machining (AEDM): A State of Art Review. *Materials and Manufacturing Processes*, 25: 1166–1180, 2010
- Lawley, A. (1978) *Powder Metallurgy Processing — New Techniques and Analyses*, Academic Press, New York, 1978
- Lee, H. T et al. (2004). Relationship between electrode size and surface cracking in the EDM machining process. *Journal of Materials Science*, 2004, Volume 39, Number 23, Pages 6981-6986
- Lee, S.H. and X.P. Li, (2001). Study of the effect of machining parameters on the machining characteristics in electrical discharge machining of tungsten carbide. *J. Mater. Process. Technol.*, 115: 344-358.
- Lonardo, P.M., and Bruzzone, A., (1999). Effect of Flushing and Electrode Material on Die Sinking EDM. *CIRP Annals - Manufacturing Technology Volume 48, Issue 1, 1999, Pages 123–126*
- Leonard B.L, Meek J.M. (1941). *The Mechanism of the Electric Spark*. The Baker and Tailor Company, London
- Liu S. (2010). *Advances in Grey Systems Research*. Scientific Publishing Services Pvt. Ltd.
- Ming, Q.Y and He,Y.L (1995). Powder-suspension dielectric fluid for EDM. *Journal of Materials Processing Technology* Volume 52, Issue 1, May 1995, Pages 44–54
- McGeough, J.A. (1988). *Advanced Methods of Machining*. Chapman and hall LtdPublishing.London

- Marafona, J.D. and Araujo,A., (2009). Influence of workpiece hardness on EDM performance. *Int J Mach Tool Manuf*, 49, 744 - 748.
- Marafona, J. and Wykes C.A., (2000). A new method of optimizing material removalrate using EDM with copper-tungsten electrodes. *Int J Mach Tools Manuf*, 40: 153 - 164.
- Marafona, J. (2007). Black layer characterisation and electrode wear ratio in electrical discharge machining (EDM). *Journal of Materials Processing Technology* 184: 1-3. 27-31 April
- Marafona, J., (2009). Black layer affects the thermal conductivity of the surface of copper tungsten electrode. *Int J Mach Tools Manuf*, 42: 482 - 488.
- Marafona, J., (2009). Black layer characterization and electrode wear ratio in electrical discharge machining (EDM). *J Mat Process Tech*, 184: 27 - 31.
- Mohri, N.; Saito, N.; Higashi, M.A.(1991). A new process of finish machining on free surface by EDM methods. *Annals of CIRP* 1991, 40 (1), 207–210.
- Ojha, K. et al.,(2011).Experimental Investigation and Modeling of PMEDM Process with Chromium Powder Suspended Dielectric. *International Journal of Applied Science and Engineering* 2011. 9, 2: 65-81
- Ojha, K. et al.,(2011). Parametric Optimization of PMEDM Process using Chromium Powder Mixed Dielectric and Triangular Shape Electrodes. *Journal of Minerals & Materials Characterization & Engineering*, Vol. 10, No.11, pp.1087-1102, 2011

- Pradhan, M.K. and Biswas, C. K. (2009). Modeling and Analysis of process parameters on Surface Roughness in EDM of AISI D2 tool Steel by RSM Approach. *World Academy of Science, Engineering and Technology* 57
- Pandey A. and Singh S. (2010). Current research trends in variants of Electrical Discharge Machining: A review. *International Journal of Engineering Science and Technology*. Vol. 2(6), 2010, 2172-2191
- Pecas, P. and Henriques,E. (2003). Influence of silicon powder-mixed dielectric on conventional electrical discharge machining. *International Journal of Machine Tools & Manufacture* 43 (2003) 1465–1471
- Pecas, P. and Henriques,E. (2008). Effect of the powder concentration and dielectric flow in the surface morphology in electrical discharge machining with powder-mixed dielectric (PMD-EDM). *Int J AdvManufTechnol* (2008) 37:1120–1132
- Pecas, P. and Henriques,E. (2003). Electrical discharge machining using simple and powder-mixed dielectric: The effect of the electrode area in the surface roughness and topography. *Journal of materials processing technology* 200 (2008) 250–258
- Prabhu, S., and Vinayagam, B.K., (2008).Analysis of Surface Characteristics of AISI D2 Tool Steel Material Using Carbon Nano Tube. *Int J Nanotech App, Volume 2, Number 1, pp. 107 - 122.*
- Prabhu, S., and Vinayagam, B.K., (2011). Modeling the machining parameters of AISI D2 tool steel material with multi wall carbon nano tube in electrical discharge machining process using response surface methodology. *International Journal of the Physical Sciences Vol. 7(2), pp. 297 – 305*

- Ramasawmy, Blunt, L. and Rajurkar, K.P. (2005), Investigation of the relationship between the white layer thickness and 3D surface texture parameters in the die sinking EDM process. *Precision Engineering Volume 29, Issue 4, October 2005, Pages 479–490*
- Rao (2009). *Manufacturing Technology Vol-Ii 2E, Volume 2*, Tata McGraw-Hill Education
- Rival (1995). Electrical Discharge Machining Of Titanium Alloy Using Copper Tungsten Electrode With Sic Powder Suspension. *Master Thesis UTM*.
- Roberts, G.A , George K., Richard L. and K (1998). *Tool Steels*, ASM International.
- Sharma, S *et al.*, (2010). Effect of aluminium powder addition in dielectric during electric discharge machining of hastelloy on machining performance using reverse polarity. *International Journal of Advanced Engineering Technology*
- Singh, S., Maheshwaria, S., Pandey P.C. (2004). Some investigations into the electric discharge machining of hardened tool steel using different electrode materials. *Journal of Materials Processing Technology Volume 149, Issues 1–3, 10 June 2004, Pages 272–277*
- Singh, S.; Maheshwari, S.; Dey, A.(2006) Electrical Discharge Machining (EDM) of aluminium metal matrix composites using powder-suspended dielectric fluid. *Journal of Mechanical Engineering 2006, 57 (5), 271–290*.
- Sutherland, K. (2008). *Filters and Filtration Handbook*. Elsevier Limited publications
- Sommer, C. (2000). Non-traditional machining handbook. First edition. Advance Publishing. Houston

Sommer, C., (2009). *Non-Traditional Machining Handbook: 2nd Edition*. Houston: Advance Publishing, Inc.

Sommer, C. and Sommer, S. (2005). *Complete EDM Handbook*, Advance Pub., 2005

Salman, O. Kayacan, M.C (2007). Evolutionary programming method for modeling the EDM parameters for roughness. *Journal of Materials Processing Technology Volume 200, Issues 1–3, 8 May 2008, Pages 347–355*

Syed K.H. and Kuppan P, (2012). Performance of electrical discharge machining using aluminium powder suspended distilled water, *Turkish Journal of Engineering and Environmental Science*, vol. 36, pp. 195-207, 2012.

Tai and Lu (2009). Improving the fatigue life of electro-discharge-machined SDK11 tool steel via the suppression of surface cracks. *International Journal of Fatigue Volume 31, Issue 3, March 2009, Pages 433–438*

Tebni, W., Boujelbene, M., Bayraktar, E. And Salem, S.B. (2008). Parametric Approach Model For Determining Electrical Discharge Machining (EDM) Conditions: Effect of Cutting Parameters on The Surface Integrity. *The Arabian Journal for Science and Engineering, Volume 34, Number 1C*

Tzeng, Y.F. and Lee, C.Y (2001). Effects of Powder Characteristics on Electro discharge Machining Efficiency. *Int J Adv Manuf Technol (2001) 17:586–592*

Tzeng, Y.F. and Chen, F.C (2003). Multi-objective optimisation of high-speed electrical discharge machining process using a Taguchi fuzzy-based approach. *Materials and Design 28 (2007) 1159–1168*

- Tzeng, Y.F. (2003). Development of a flexible high-speed EDM technology with geometrical transform optimization. *Journal of materials processing technology* 203 (2008) 355–364
- Tzeng, Y.F. and Chen F.C., (2005). Investigation into some surface characteristics of electrical discharge machined SKD-11 using powder-suspension dielectric oil. *J Mat Process Technol*, 170: 385-391.
- Tzeng, Y. F.; Chen, F. C. (2007). Multi-objective optimization of high-speed electrical discharge machining process using a Taguchi fuzzy-based approach, *Materials and Design*, Vol. 28, No. 4, 1159–1168
- Uno, Y., Okada, A., and Cetin S., (2001). Study on the Distribution of Scattered Debris Generated by a Single Pulse Discharge in EDM Process. *Design and Production of Dies and Molds*, 2001
- Volk, M.W., (1996). *Pump characteristics and applications*, New York : Marcel Dekker
- Wong, Y.S., Lim, L.C., Lee, L.C., (1995). Effect of flushing on electro-discharge machined surfaces. *Journal of Materials Processing Technology* 48, 299 - 305.
- Wong, Y.S., Lim, L.C.; Iqbal, R.; Tee, W.M. (1998) Near-mirror-finish phenomenon in EDM using powder-mixed dielectric. *Journal of Materials Processing Technology* 1998, 79 (1–3), 30–40.
- Wu, K.L. et al. (2005). Improvement of surface finish on SKD steel using electro-discharge machining with aluminum and surfactant added dielectric. *International Journal of Machine Tools & Manufacture* 45 (2005) 1195–1201

Yan, B.H.; Chen, S.L. (1993). Effects of dielectric with suspended aluminum powder on EDM. *Journal of Chinese Society of Mechanical Engineering* 1993, 14 (3), 307–312.

Yeo, S.H. , Tan,P.C. and W Kurnia., (2007). Effects of powder additives suspended in dielectric on crater characteristics for micro electrical discharge machining. *J. Micromech. Microeng.* 17 (2007) N91–N98

Yu, C.P.; Chen, W.C.; Chang, S.W.; Chang, C.C.(1996). Effects of the concentration of suspended aluminum powder in dielectric fluid on EDM of carbide of tungsten. *Proceedings of the 13th Conference of Chinese Society of Mechanical Engineers,Taiwan, 1996; 445–450.*

Zhao, W.S.; Meng, Q.G.; Wang, Z.L (2002). The application of research on powder mixed EDM in rough machining. *Journal of Materials Processing Technology* 2002, 129 (1–3), 30–33.



PTTAUTHM
PERPUSTAKAAN TUNKU TUN AMINAH